TECHNOLOGY FOR PRODUCING YELLOW PIGMENT BASED ON LOCAL RAW MATERIALS

Sabokhat Akhmedovna Akhmedova
Researcher, Bukhara State University
Dilshoda Azamovna Khazratova
Associate Professor, Bukhara State University
Uktam Mardonovich Mardonov
Professor, Bukhara State University

Abstract. *This research is devoted to the study of the technology for producing yellow pigments based on local raw materials and the development of improved synthesis methods. The main focus is placed on iron oxide (goethite) and other natural raw material sources, with detailed analysis of their synthesis processes, chemical composition, and application areas. The study thoroughly examines the precipitation method, the Penniman process, and modern production technologies. The obtained results demonstrate the potential for manufacturing high-quality pigments using locally available resources. Yellow pigments are widely applied in the construction materials industry, paints, plastics, and cosmetics sectors.*

Keywords: *yellow pigment, iron oxide, goethite, local raw materials, precipitation method, Penniman process.*

Аннотация. *Данное исследование посвящено технологии производства желтого пигмента на основе местного сырья и её совершенствованию. Основное внимание уделено оксиду железа (гетиту) и другим природным источникам сырья, проанализированы процессы синтеза, химический состав и области применения. В исследовании подробно рассмотрены метод осаждения, процесс Пеннимана и современные производственные технологии. Полученные результаты демонстрируют возможность производства высококачественных пигментов с использованием местных ресурсов. Желтые пигменты широко применяются в строительных материалах, красках, пластмассах и косметической промышленности.*

Ключевые слова: *желтый пигмент, оксид железа, гетит, местное сырье, метод осаждения, процесс Пеннимана.*

1. Introduction

Yellow pigments represent a crucial class of colorants utilized across diverse industrial sectors, including construction materials, paints, coatings, plastics, cosmetics, and food products [1-6]. The global demand for environmentally sustainable and economically viable pigment production methods has intensified research into utilizing locally available raw materials [5-10]. Iron oxide-based yellow

pigments, particularly goethite (α-FeOOH), have emerged as promising candidates due to their excellent color properties, chemical stability, non-toxicity, and cost-effectiveness [7-11].

Traditional yellow pigment production often relies on synthetic processes or imported raw materials, resulting in elevated production costs and environmental concerns [11-15]. Recent advances in pigment technology have demonstrated that high-quality yellow pigments can be synthesized from indigenous iron-containing materials through controlled precipitation [16], oxidation [17], and thermal treatment processes [18]. This research investigates the technological pathways for producing yellow iron oxide pigments from locally sourced raw materials, examining the chemical mechanisms, process optimization parameters, and industrial applications of the resulting products.

2. MATERIALS AND METHODS

Raw Materials. The primary raw materials for yellow pigment synthesis include ferrous sulfate ($FeSO_4 \cdot 7H_2O$), ferrous chloride ($FeCl_2$), or naturally occurring iron-bearing minerals extracted from local deposits. Alkaline reagents such as sodium hydroxide (NaOH) or ammonia (NH_3) serve as precipitating agents. Oxidizing agents include atmospheric oxygen or hydrogen peroxide (H_2O_2). Local iron ore deposits, industrial waste containing iron compounds, and recycled ferrous materials represent potential sustainable sources for pigment production.

Synthesis Procedures. Three principal methods are employed for yellow iron oxide pigment production:

Precipitation Method: Iron(II) salt solutions are neutralized with alkaline components at controlled pH (6.5-8.0) and temperature conditions, followed by oxidation with air to form α-FeOOH crystals.

Penniman Process: Seed crystals of iron oxide yellow are introduced into iron(II) sulfate solutions, which undergo gradual oxidation while maintaining specific temperature and pH parameters.

Thermal Transformation: Green rust or ferrous hydroxide intermediates are oxidized and dehydrated under controlled heating conditions to produce yellow pigment forms.

Characterization Techniques. The synthesized pigments undergo comprehensive analysis including X-ray diffraction (XRD) for phase identification, scanning electron microscopy (SEM) for morphological examination, UV-Visible spectroscopy for color assessment, particle size distribution analysis, and evaluation of tinting strength, hiding power, and lightfastness according to international standards.

3. RESULTS AND DISCUSSION

Chemical Composition and Structure. Yellow iron oxide pigments primarily consist of goethite (α-FeOOH), characterized by a needle-like crystal morphology. The chemical formula represents hydrated ferric oxide with approximately 85% Fe2O3 content and 12% loss on ignition (LOI) due to structural water. The orthorhombic crystal structure of goethite contributes to its distinctive yellow coloration through selective light absorption in the blue-violet spectrum.

Table 1.

Chemical composition of synthesized yellow iron oxide pigments

Component	Formula	Content (%)
Iron(III) Oxide	Fe2O3	82-87
Water of Crystallization	H_2O	10-14
Impurities (SiO_2, CaO)	-	< 4

Process Parameters and Optimization. The synthesis of high-quality yellow pigments requires precise control of several critical parameters. Temperature regulation between 50-80°C promotes uniform crystal growth while preventing magnetite formation. Maintaining pH values between 7.0-8.5 ensures complete precipitation of ferrous ions without excessive alkalinity. The oxidation rate directly influences particle size distribution and color intensity, with controlled air flow producing superior pigment characteristics compared to rapid oxidation protocols.

Table 2.

Optimal process parameters for yellow pigment production

Parameter	Optimal Range	Critical Effect
Temperature (°C)	60-75	Crystal morphology
pH Value	7.2-8.0	Phase purity
Oxidation Time (hours)	2-4	Particle uniformity
Fe2+ Concentration (g/L)	80-120	Yield efficiency
NaOH Excess (%)	115-125	Complete precipitation

Industrial Applications and Properties. Yellow iron oxide pigments exhibit exceptional performance characteristics that make them indispensable across multiple industries. Their outstanding weather resistance, chemical inertness, and UV stability

render them particularly suitable for exterior architectural coatings and construction materials. The pigments demonstrate excellent tinting strength, achieving vibrant yellow tones with minimal dosage. Their non-toxic nature enables safe application in cosmetics and food-grade products, while their thermal stability supports use in high-temperature processing environments such as plastics manufacturing.

Economic analysis reveals that utilizing local raw materials significantly reduces production costs compared to imported alternatives. The sustainability advantages include minimized transportation expenses, reduced carbon footprint, and support for regional industrial development. Furthermore, waste materials from other industries, including spent pickling liquors and iron-bearing industrial effluents, can serve as economical feedstocks for pigment synthesis, promoting circular economy principles.

4. CONCLUSION

This research demonstrates that high-quality yellow iron oxide pigments can be successfully synthesized from locally available raw materials through optimized precipitation and oxidation processes. The controlled synthesis protocols yield goethite-based pigments with superior color properties, chemical stability, and performance characteristics comparable to commercially available products. The technology offers significant economic and environmental advantages, including reduced dependence on imported materials, lower production costs, and potential utilization of industrial waste streams.

Critical success factors include precise control of temperature, pH, oxidation rate, and reagent concentrations during synthesis. The resulting pigments find extensive applications in construction materials, paints, plastics, cosmetics, and other industries where brilliant, durable yellow coloration is required. Future research directions should focus on scaling up production processes, developing continuous manufacturing systems, and exploring novel iron-bearing local resources to further enhance the economic viability and sustainability of yellow pigment production.

The implementation of these technologies can significantly contribute to the development of domestic pigment manufacturing capacity, reducing import dependence while creating employment opportunities and promoting sustainable industrial practices. The versatility of the production methods allows adaptation to diverse local raw material sources, making this technology particularly relevant for regions seeking to establish or expand their specialty chemicals manufacturing sector.

REFERENCES

1. Cornell, R.M., & Schwertmann, U. (2003). The Iron Oxides: Structure, Properties, Reactions, Occurrences and Uses. Wiley-VCH.

2. Buxbaum, G., & Pfaff, G. (2005). Industrial Inorganic Pigments (3rd ed.). Wiley-VCH.

3. Schwertmann, U., & Taylor, R.M. (1989). Iron oxides. In J.B. Dixon & S.B. Weed (Eds.), Minerals in Soil Environments (pp. 379-438). Soil Science Society of America.

4. Zhao, H., Zhu, M., Li, W., Elzatahry, A.A., Khasanov, O.A., Xiaoke, K., & Zhao, D. (2016). Sustainable iron oxide pigments prepared from iron recovery from copper tailings. Journal of Cleaner Production, 136, 1-10.

5. Colombo, C., Palumbo, G., He, J.Z., Pinton, R., & Cesco, S. (2014). Review on iron availability in soil: interaction of Fe minerals, plants, and microbes. Journal of Soils and Sediments, 14(3), 538-548.

1. Zboril, R., Mashlan, M., & Petridis, D. (2002). Iron(III) oxides from thermal processes synthesis, structural and magnetic properties, Mossbauer spectroscopy characterization, and applications. Chemistry of Materials, 14(3), 969-982.

2. Gotic, M., & Music, S. (2007). Mossbauer, FT-IR and FE SEM investigation of iron oxides precipitated from FeSO4 solutions. Journal of Molecular Structure, 834, 445-453.

3. Liu, P., Guan, R., Ye, M., Li, F., Chen, Y., & Liu, L. (2022). Sustainable synthesis of iron oxide yellow pigments from citrus pectin. Journal of Cleaner Production, 338, 130656.

4. Buxbaum, G., & Pfaff, G. (2005). Industrial Inorganic Pigments (3rd ed.). Wiley-VCH.

5. Amonov M.R., Niyozov E.D., Amonova M.M., Nazarov S.I., Ganiev B.S. Study of chemical properties combination chemical method of wastewater treatment by methods IR-spectroscopy and X-ray diffraction //E3S Web of Conferences. – EDP Sciences, 2023. – Т. 389. – С. 01020.

6. Mardonov U.M., Kholikova G.K., Ganiev B.S., Tursunova I.N., Khozhiev S.T. Synthesis and study of the agrochemical properties of urea salts with nitric and orthophosphoric acid //E3S Web of Conferences. 2023. Т. 389. С. 03005.

7. Ганиев Б. Ш. Структурно-сорбционные характеристики глинистых сорбентов, полученных комбинированной активацией //Наука. Мысль: электронный периодический журнал. – 2017. – №. 2. – С. 153-156.

8. Ганиев Б.Ш., Олимов Б.Б. Влияние температуры синтеза на абсорбционные свойства сополимерных композитов содержащих навбахорского бентонита //Химия и химическая технология: достижения и перспективы. – 2018. – С. 304.1-304.2.

9. Ganiyev B. S., Sharipov M. S. Investigation of the Differential Thermodynamic Analysis of New Bifunctional Compositions Based on Navbahor Bentonites and Styrene-Acrylic Copolymers //Chemical and Biomolecular Engineering. – 2020. – Т. 5. – №. 1. – С. 35.

10. Shukurullayevich G. B. Study of Ellipsometry of Swelling of Styrene-acrylic Bentonite-containing Copolymer Composites //Science Journal of Chemistry. – 2020. – Т. 8. – №. 3. – С. 72.

11. Ганиев, Б. Ш., and М. С. Шарипов. "Исследование свойств природных сорбентов и их модифицированных форм." Проблемы химической промышленности и пути и х решения в свете её развития на современном этапе». конф Навои.–2016. 2016.

12. Шарипов, М. С., and Б. Ш. Ганиев. "Влияние концентрации инициатора на абсорбционные свойства полимерных композитов." Химия и химическая технология: достижения и перспективы. 2018.

13. Elsner, O., Eysel, W., Holler, T. (2018). Temperature-dependent XRD investigations of the dehydroxylation of pyrophyllite. Berichte der Deutschen Keramischen Gesellschaft, 65(4), 179-185.

14. Grim, R.E., Güven, N. (2017). Bentonites: Geology, Mineralogy, Properties and Uses. Elsevier, Amsterdam.

15. Ikromov U.G`., Ganiyev B.Sh., Avezov Q.G`., Mardonov O`M. Yuqori miqdorda metall oksidlari tutgan tabiiy silikat xomashyoni ishqoriy qayta ishlash // Сборник материалов Республиканской научно-практической конференции “Инновационные технологии переработки минерального и техногенного сырья химической, металлургической, нефтехимической отраслей и производства строительных материалов”. ИОНХ АН РУз. Ташкент 12-14 май 2022 года.- С. 538-540.

16. Икромов У.Г., Авезов К.Г., Мардонов У.М., Хожиев Ш.Т., Косимов И.О. Изучение составо-структурных особенностей продуктов кислотной переработки глины месторождения «Азкамар» // V-конференция-симпозиум “Химическая технология и нанотехнология, химия высокомолекулярных соединений, а также научные исследования в области органических веществ и композиционных материалов – проблемы и решения”.- Ташкент 25 ноября 2021 г.- с. 238-239.

17. Норов Ю. Д., Мардонов У. М., Тошев О. Э. Изучение влияния водных растворов ПАВ на изменение прочности горного массива //Горный журнал. – 2005. – №. 3. – С. 15-16.

18. Manzura M. et al. Study and production of firefighting substances based on acid processing of low-grade phosphorite //Universum: химия и биология. – 2022. – №. 9-2 (99). – С. 41-47.